



Fluorosint® PTFE Family of Advanced Fluoropolymer Materials



FLUOROSINT ENHANCED PTFE MATERIALS

See How These Materials Stack Up In Your Application

Quadrant developed the Fluorosint range of enhanced PTFE materials to fill the performance gaps where unfilled and low-tech, filled PTFE based polymers underperform. Each Fluorosint material was specifically developed to excel in demanding bearing and seal applications. While each of these materials possess the chemical resistance and compliance of PTFE, each material offers some special benefits that give the designer clear performance advantages.




TABLE OF CONTENTS

Fluorosint® 500 Enhanced PTFE	3
Fluorosint® 207 Enhanced, FDA-Compliant PTFE	.4
Fluorosint® HPV Wear Resistant, FDA-Compliant PTFE	.5
Fluorosint® MT-01 Ultra-High Performance, Enhanced PTFE	6
Physical Property Data	7



FLUOROSINT® 500

Exceptional Dimensional Stability for Precise Tolerance Control

Key Benefits

Fluorosint 500 Enhanced PTFE offers an ideal combination of stability and wear-resistance for sealing applications where tight dimensional control is required. Fluorosint 500 also greatly reduces the risk of a catastrophic system failure by becoming a sacrificial wear surface. With a deformation under load 9 times lower than virgin PTFE, Fluorosint 500 allows designers to greatly improve the efficiency of systems without sacrificing the wear resistance and forgiving benefits of PTFE. The synthetic mica developed and manufactured by Quadrant delivers tolerance performance approximating that of aluminum.



Light Tan / Grey




Common Applications


- · Split and one-piece seals
- · Valve seats
- Shrouds
- Slide bearings
- Wear strips
- · Sacrificial, abradable seals
- Thrust washers

APPLICATION EXAMPLE

Fluorosint 500 has been used very successfully as a replacement for metal/aluminum seals and shrouds in compressors. In addition to the security a sacrificial part provides the system, Fluorosint 500 allows the introduction of abradable sealing technology where mating parts are allowed to "cut" their own running clearance and thus permitting significant gains in efficiency.

Fluorosint 500







FLUOROSINT® 207

Lowest Coefficient of Friction of Fluorosint® Grades

Key Benefits

FDA compliant Fluorosint 207 Enhanced PTFE is a significant performance upgrade for any designer using PTFE for applications where temperature resistance, chemical resistance and FDA compliance are all important. Fluorosint 207 lasts far longer than unfilled PTFE in wear applications and has an extremely low coefficient of friction. Fluorosint 207 works well against most mating surfaces.

Common Applications

- Seals
- Mixers
- Pumps
- Appliances
- Bearings
- · Valve seats

APPLICATION EXAMPLE

Fluorosint 207 replaces unfilled PTFE and low-tech, filled PTFE's in wear and seal applications where either stability or wear resistance are causing failures. A commercial beverage filling system replaced virgin PTFE seals with Fluorosint 207 and improved fill accuracy associated with


leaks caused by failed seals.







Fluorosint 207





FLUOROSINT® HPV

Most Wear Resistant Fluorosint Grade - Outlasts Low-tech PTFE Based Materials

Key Benefits

FDA compliant Fluorosint HPV is a high performance bearing grade of Fluorosint - optimized for high PV and very low "K", or wear factor. Fluorosint HPV was developed for bearing applications where other, low-tech PTFE formulations exhibit premature wear or simply cannot perform. FDA compliance gives food and pharmaceutical equipment manufacturers new design options and all benefit from its excellent load bearing and wear characteristics.

FDA

Light Tan / Grey

Common Applications


- · Bearings
- · Commercial food equipment
- · Wear guides
- · High performance seals
- Thrust washers


APPLICATION EXAMPLE

Fluorosint HPV was specified by a manufacturer of commercial sausage production equipment as a replacement for a low-tech filled PTFE material. The old material would wear quickly and not properly stretch the product during filling. The premature wear caused tears in the product and required frequent replacement. An additional benefit of Fluorosint HPV – improved dimensional stability – allowed designers to remove a press fit metal part that was required to compensate for the low-tech material's lack of dimensional control.



Fluorosint HPV





Dark Grey

FLUOROSINT® MT-01

Ultra-High Performance Grade For Stability At Elevated Temperature

Key Benefits

Fluorosint MT-01 is an extreme service grade developed specifically for applications where the benefits of PTFE-based materials also require strength, stiffness and stability. Fluorosint MT-01 delivers high mechanical performance at elevated temperature and as a result is often specified in seat, seal and wear applications where extreme conditions are present.



Common Applications

- High temperature seals
- · Linear guides
- Wear bands

FLUOROSINT® MT-01

FLUOROSINT® 500

RULON® J

25% GLASS FILLED PTFE

PTFE

FLUOROSINT® HPV

% deformation at 2000 psi, 122°F (50°C)

55% BRONZE, 5% MoS₂, PTFE

FLUOROSINT® 207

Ovens and dryers

APPLICATION EXAMPLE


Deformation Under Load

Fluorosint MT-01 is widely specified in chemical processing equipment like the aggressive environment present during sour gas processing. Fluorosint MT-01 extends the temperature envelope of PTFE and provides remarkable stability for applications that see extremes. Seals, replaced monthly in oil recovery equipment have been replaced with Fluorosint MT-01 and now outlast other components.









Fluorosint MT-01

Fluorosint

Physical Properties

PHYSICAL PROPERTY DATA

2 3 4 5 6 7 7 8 9 10 11 12 13 14	Specific Gravity, 73°F. Tensile Strength, 73°F. Tensile Modulus of Elasticity, 73°F. Tensile Elongation (at break), 73°F. Flexural Strength, 73°F. Flexural Modulus of Elasticity, 73°F. Shear Strength, 73°F. Compressive Strength, 10% Deformation, 73°F. Compressive Modulus of Elasticity, 73°F. Deformation Under Load, % def @ 2,000 PSI, 122°F (50°C) Hardness, Rockwell, Scale as noted, 73°F. Hardness, Durometer, Shore "D" Scale, 73°F. Izod Impact (notched), 73°F., ft. lb./in. of notch Coefficient of Friction (Dry vs. Steel) Dynamic Limiting PV (with 4:1 safety factor applied)	D792 D638 D638 D638 D790 D790 D732 D695 D695 - D785 D2240 D256 Type "A" QTM55007	2.32 1,100 300,000 30 2,200 500,000 2,100 4,000 250,000 5.0% R55 D70 0.9	2.3 1,500 250,000 50 2,000 350,000 1,700 3,800 225,000 1.1% R50	2.06 1,450 210,000 90 2,500 165,000 2,500 3,000 110,000 3.2% R44 D64	2.27 2,100 326,000 40 4,000 488,000 2,600 3,400 250,000 0.2% R74 D75
3 4 5 6 7 7 8 9 10 11 12 13 14	Tensile Modulus of Elasticity, 73°F. Tensile Elongation (at break), 73°F. Flexural Strength, 73°F. Flexural Modulus of Elasticity, 73°F. Shear Strength, 73°F. Compressive Strength, 10% Deformation, 73°F. Compressive Modulus of Elasticity, 73°F. Deformation Under Load, % def @ 2,000 PSI, 122°F (50°C) Hardness, Rockwell, Scale as noted, 73°F. Hardness, Durometer, Shore "D" Scale, 73°F. Izod Impact (notched), 73°F., ft. lb./in. of notch Coefficient of Friction (Dry vs. Steel) Dynamic Limiting PV (with 4:1 safety factor applied)	D638 D638 D790 D790 D792 D695 D695 - D785 D2240 D256 Type "A"	300,000 30 2,200 500,000 2,100 4,000 250,000 5.0% R55 D70	250,000 50 2,000 350,000 1,700 3,800 225,000 1.1% R50	210,000 90 2,500 165,000 2,500 3,000 110,000 3.2% R44	326,000 40 4,000 488,000 2,600 3,400 250,000 0.2% R74
4 5 6 7 7 8 9 10 11 12 13 14	Tensile Elongation (at break), 73°F. Flexural Strength, 73°F. Flexural Modulus of Elasticity, 73°F. Shear Strength, 73°F. Compressive Strength, 10% Deformation, 73°F. Compressive Modulus of Elasticity, 73°F. Deformation Under Load, % def @ 2,000 PSI, 122°F (50°C) Hardness, Rockwell, Scale as noted, 73°F. Hardness, Durometer, Shore "D" Scale, 73°F. Izod Impact (notched), 73°F., ft. lb./in. of notch Coefficient of Friction (Dry vs. Steel) Dynamic Limiting PV (with 4:1 safety factor applied)	D638 D790 D790 D732 D695 D695 - D785 D2240 D256 Type "A"	30 2,200 500,000 2,100 4,000 250,000 5.0% R55 D70	50 2,000 350,000 1,700 3,800 225,000 1.1% R50	90 2,500 165,000 2,500 3,000 110,000 3.2% R44	40 4,000 488,000 2,600 3,400 250,000 0.2% R74
5 6 7 8 9 10 11 12 13 14	Flexural Strength, 73°F. Flexural Modulus of Elasticity, 73°F. Shear Strength, 73°F. Compressive Strength, 10% Deformation, 73°F. Compressive Modulus of Elasticity, 73°F. Deformation Under Load, % def @ 2,000 PSI, 122°F (50°C) Hardness, Rockwell, Scale as noted, 73°F. Hardness, Durometer, Shore "D" Scale, 73°F. Izod Impact (notched), 73°F., ft. lb./in. of notch Coefficient of Friction (Dry vs. Steel) Dynamic Limiting PV (with 4:1 safety factor applied)	D790 D790 D732 D695 D695 - D785 D2240 D256 Type "A"	2,200 500,000 2,100 4,000 250,000 5.0% R55 D70	2,000 350,000 1,700 3,800 225,000 1.1% R50	2,500 165,000 2,500 3,000 110,000 3.2% R44	4,000 488,000 2,600 3,400 250,000 0.2% R74
WECHANICAL 10 11 12 13 14	Flexural Modulus of Elasticity, 73°F. Shear Strength, 73°F. Compressive Strength, 10% Deformation, 73°F. Compressive Modulus of Elasticity, 73°F. Deformation Under Load, % def @ 2,000 PSI, 122°F (50°C) Hardness, Rockwell, Scale as noted, 73°F. Hardness, Durometer, Shore "D" Scale, 73°F. Izod Impact (notched), 73°F., ft. lb./in. of notch Coefficient of Friction (Dry vs. Steel) Dynamic Limiting PV (with 4:1 safety factor applied)	D790 D732 D695 D695 - D785 D2240 D256 Type "A"	500,000 2,100 4,000 250,000 5.0% R55 D70	350,000 1,700 3,800 225,000 1.1% R50	165,000 2,500 3,000 110,000 3.2% R44	488,000 2,600 3,400 250,000 0.2% R74
7 8 9 10 11 12 13 14	Shear Strength, 73°F. Compressive Strength, 10% Deformation, 73°F. Compressive Modulus of Elasticity, 73°F. Deformation Under Load, % def @ 2,000 PSI, 122°F (50°C) Hardness, Rockwell, Scale as noted, 73°F. Hardness, Durometer, Shore "D" Scale, 73°F. Izod Impact (notched), 73°F., ft. lb./in. of notch Coefficient of Friction (Dry vs. Steel) Dynamic Limiting PV (with 4:1 safety factor applied)	D732 D695 D695 - D785 D2240 D256 Type "A"	2,100 4,000 250,000 5.0% R55 D70	1,700 3,800 225,000 1.1% R50	2,500 3,000 110,000 3.2% R44	2,600 3,400 250,000 0.2% R74
11 12 13 14	Compressive Strength, 10% Deformation, 73°F. Compressive Modulus of Elasticity, 73°F. Deformation Under Load, % def @ 2,000 PSI, 122°F (50°C) Hardness, Rockwell, Scale as noted, 73°F. Hardness, Durometer, Shore "D" Scale, 73°F. Izod Impact (notched), 73°F., ft. lb./in. of notch Coefficient of Friction (Dry vs. Steel) Dynamic Limiting PV (with 4:1 safety factor applied)	D695 D695 - D785 D2240 D256 Type "A"	4,000 250,000 5.0% R55 D70	3,800 225,000 1.1% R50	3,000 110,000 3.2% R44	3,400 250,000 0.2% R74
11 12 13 14	Compressive Modulus of Elasticity, 73°F. Deformation Under Load, % def @ 2,000 PSI, 122°F (50°C) Hardness, Rockwell, Scale as noted, 73°F. Hardness, Durometer, Shore "D" Scale, 73°F. Izod Impact (notched), 73°F., ft. lb./in. of notch Coefficient of Friction (Dry vs. Steel) Dynamic Limiting PV (with 4:1 safety factor applied)	D695 - D785 D2240 D256 Type "A"	250,000 5.0% R55 D70	225,000 1.1% R50	110,000 3.2% R44	250,000 0.2% R74
11 12 13 14	Deformation Under Load, % def @ 2,000 PSI, 122°F (50°C) Hardness, Rockwell, Scale as noted, 73°F. Hardness, Durometer, Shore "D" Scale, 73°F. Izod Impact (notched), 73°F., ft. lb./in. of notch Coefficient of Friction (Dry vs. Steel) Dynamic Limiting PV (with 4:1 safety factor applied)	- D785 D2240 D256 Type "A"	5.0% R55 D70	1.1% R50	3.2% R44	0.2% R74
11 12 13 14	Hardness, Rockwell, Scale as noted, 73°F. Hardness, Durometer, Shore "D" Scale, 73°F. Izod Impact (notched), 73°F., ft. lb./in. of notch Coefficient of Friction (Dry vs. Steel) Dynamic Limiting PV (with 4:1 safety factor applied)	D785 D2240 D256 Type "A"	R55 D70	R50	R44	R74
12 13 14	Hardness, Durometer, Shore "D" Scale, 73°F. Izod Impact (notched), 73°F., ft. lb./in. of notch Coefficient of Friction (Dry vs. Steel) Dynamic Limiting PV (with 4:1 safety factor applied)	D2240 D256 Type "A"	D70		1	
13 14	Izod Impact (notched), 73°F., ft. lb./in. of notch Coefficient of Friction (Dry vs. Steel) Dynamic Limiting PV (with 4:1 safety factor applied)	D256 Type "A"		D65	D64	D75
14	Coefficient of Friction (Dry vs. Steel) Dynamic Limiting PV (with 4:1 safety factor applied)	30.000.00037.000 • • 10.0010.010	0.9	775	501	
	Limiting PV (with 4:1 safety factor applied)	QTM55007		1	1.8	0.8
15			0.15	0.1	0.15	0.18
		QTM55007	8,000	8,000	20,000	4,500
16	Wear Factor "k" x 10 -10	QTM55010	600	30	38	200
17	Coefficient of Linear Thermal Expansion (-40°F to 300°F)	E-831 (TMA)	2.5 x10 ⁵	5.7 x10 ⁻⁵	4.9 x10 ⁻⁵	3.0 x10 ⁻⁵
H 18	Heat Deflection Temperature 264 psi	D648	270	210	180	200
19 20 18 18 18 18 18 18 18 18 18 18 18 18 18	Tg-Glass transition (amorphous)	D3418	N/A	N/A	N/A	N/A
丑 20	Melting Point (crystalline) peak	D3418	621	621	621	
	Continuous Service Temperature in Air (Max.) (1)	8	500	500	500	600
22	Thermal Conductivity	F433	5.3			
23	Dielectric Strength, Short Term	D149	275	200	(+)	-
24	Surface Resistivity	EOS/ESD S 11.11	>1013	>1012	>1013	<105
23 24 25 26	Dielectric Constant, 10 6 Hz	D150	2.85	2.65	.#×	-
26	Dissipation Factor, 10 6 Hz	D150	0.008	0.008	-	
	Flammability @ 3.1 mm (1/8 in.) (5)	UL94	V-0	V-0	V-0	V-0
28	Water Absorption Immersion, 24 Hours	D570 (2)	0.1	0.03	0.15	0.1
29	Water Absorption Immersion, Saturation	D570 (2)	3	0.2	0.43	-
30	Acids, Weak, acetic, dilute hydrochloric or sulfuric acid	~	Α	Α	Α	Α
31	Acids, Strong, conc. hydrochloric or sulfuric acid	•	Α	Α	Α	Α
2 32	Alkalies, Weak, dilute ammonia or sodium hydroxide	3	Α	Α	А	А
33	Alkalies, Strong, strong ammonia or sodium hydroxide	- 1	U	U	U	Α
33 34 35	Hydrocarbons-Aromatic, benzene, toluene	*	Α	Α	A	A
当 35	Hydrocarbons-Aliphatic, gasoline, hexane, grease	2	Α	Α	Α	Α
36	Ketones, esters, acetone, methyl ethyl ketone	-	А	Α	A	A
37	Ethers, diethyl ether, tetrahydrofuran	Œ.	А	Α	Α	Α
38	Chlorinated Solvents, methylene chloride, chloroform		А	Α	Α	Α
39	Alcohols, methanol, ethanol, anti-freeze		А	Α	A	А
40	Continuous Sunlight	-	А	Α	А	Α
ec 41	FDA Compliance		N	Y	Y	N
42 42	Relative Cost (4)	22	\$\$	\$\$\$	\$\$\$	\$\$\$\$
6 43	Relative Machinability (1-10, 1=Easier to Machine)	ir.	2	2	2	5

Distributed by:		

Learn more online at www.quadrantplastics.com

Quadrant has extensive product and machining resources available online. Our website is a portal to a wealth of technical data and the easiest way to engage our application specialists. Our team stands ready to help offer solutions to your toughest problems.

Quadrant Engineering Plastic Products Worldwide

EUROPE

Quadrant EPP AG Hardstrasse 5 CH-5600 Lenzburg Tel +41 (0) 62 8858259 Fax +41 (0) 62 8858401 e-mail: info@gplas.com

NORTH AMERICA

2120 Fairmont Avenue PO Box 14235 - Reading, PA 19612-4235 Tel 800 366 0300 / +1 610 320 6600 Fax 800 366 0301 / +1 610 320 6868 e-mail: americas.epp@qplas.com

ASIA-PACIFIC

60 Ha Mei San Tsuen, Ping Shan Yuen Long - N.T. Hong Kong Tel +852 (0) 24702683 Fax +852 (0) 24789966 e-mail: asia.epp@qplas.com

BELGIUM • FRANCE • GERMANY • HONG KONG • HUNGARY • INDIA • ITALY • JAPAN • KOREA • MEXICO • POLAND SOUTH AFRICA • SWITZERLAND • THE NETHERLANDS • UNITED KINGDOM • UNITED STATES OF AMERICA

All statements, technical information and recommendations contained in this publication are presented in good faith, based upon tests believed to be reliable and practical field experience. The reader is cautioned, however, that Quadrant Engineering Plastic Products does not guarantee the accuracy or completeness of this information and it is the customer's responsibility to determine the suitability of Quadrant's products in any given application.

Acetron, Duraspin, Duratron, Erta, Ertacetal, Ertalene, Ertalon, Ertalyte, Extreme Materials, Fluorosint, Ketron, MC, Monocast, Novatron, Nylatrack, Nylatron, Polypenco, Proteus, Sanalite, Semitron, Techtron, TIVAR, Ultrawear and Vibratuf are registered trademarks of the Quadrant group of companies.

*Rulon is a registered trademark of Saint Gobain Performance Plastics

